

Lonwood Marine is Lonseal's collection of high-performance, slip-resistant marine vinyl safety flooring. The different products cover a range of colors, styles and surface attributes. All Lonwood Marine products feature: flexible vinyl sheet construction allowing for moisture-free seams, baseboard coving and vertical surface applications; low-maintenance finish that eliminates re-finishing expenses; durable wear-layer that stands up to years of usage in marine environments; and coordinating trim available for hatch covers and access panels.

STANDARD SIZES (nominal)
Overall thickness: 0.080" (2.0 mm)
Wear layer thickness: 0.031" (0.8 mm)

Roll Size: 6' (1.8 m) wide x 60' (18.3 m)
Weight: See individual weights below
Styles: Six available

5-Year Warranty

TECHNICAL DATA

| Product | Static Coefficient of Friction ASTM C 1028 | Critical Radiant Flux | Abrasion Resistance | Static Load Limit (ASTM F 970) – Modified | Chemical Resistance (ASTM F 925) |
|--|---|--|--|---|--|
| MAPLE & TEAK Weight: .63 lb/sq. ft., 225 lbs/roll | 0.74 Wet 0.72 Dry | (ASTM E 648) Class 1 per NFPA Life Safety Code 101 | (ASTM D 3884) Net weight Loss after 1000 revolutions: 0.35% | 1,300 psi residual compression of 0.005" | NO Change: 5% Ammonia, 5% Acetic Acid, 70% Isopropyl Alcohol, 5% Sodium Hydroxide, 5% Hydrochloric Acid, Mineral Oil, Bleach, Sulfuric Acid, Olive Oil, 5% Phenol, Gasoline Kerosene |
| TEAK & HOLLY GLOSS Weight: .63 lb/sq. ft., 225 lbs/roll | 0.68 Wet 0.71 Dry | (ASTM E 648) Class 1 per NFPA Life Safety Code 101 | (ASTM D 3884) Net weight Loss after 1000 revolutions: 0.50% | 500 psi residual compression of 0.005" | NO Change: 5% Ammonia, 5% Acetic Acid, 70% Isopropyl Alcohol, 5% Sodium Hydroxide, 5% Hydrochloric Acid, Mineral Oil, Bleach, Sulfuric Acid, Kerosene, Olive Oil, Gasoline Slight Surface Attack: 5% Phenol |
| MAHOGHANY & HOLLY Weight: .58 lb/sq. ft., 210 lbs/roll | 0.83 Wet 0.92 Dry | (ASTM E 648) Class 1 per NFPA Life Safety Code 101 | (ASTM D 3884) Net weight Loss after 1000 revolutions: 0.23% | 1,100 psi residual compression of 0.005" | NO Change: 5% Ammonia, 5% Acetic Acid, 70% Isopropyl Alcohol, 5% Sodium Hydroxide, 5% Hydrochloric Acid, Mineral Oil, Bleach, Sulfuric Acid, Kerosene, Olive Oil, 5% Phenol Slight Color Change: Gasoline |
| TEAK & HOLLY with TOPSEAL Weight: .63 lb/sq. ft., 225 lbs/roll | 0.94 Wet 0.74 Dry | (ASTM E 648) Class 1 per NFPA Life Safety Code 101 | (ASTM D 3884) Net weight Loss after 1000 revolutions: 0.40% | 1,300 psi residual compression of 0.005" | NO Change: 5% Ammonia, 5% Acetic Acid, 70% Isopropyl Alcohol, 5% Sodium Hydroxide, 5% Hydrochloric Acid, Mineral Oil, Bleach, Sulfuric Acid, Kerosene, Olive Oil, Gasoline Slight Surface Dulling, Slight Surface Attack, Slight Color Change: 5% Phenol |
| TEAK & EBONY Weight: .58 lb/sq. ft., 210 lbs/roll | 1.04 Wet 0.98 Dry | (ASTM E 648) Class 1 per NFPA Life Safety Code 101 | (ASTM D 3884) Net weight Loss after 1000 revolutions: 0.36% | 1,100 psi residual compression of 0.005" | NO Change: 5% Ammonia, 5% Acetic Acid, 70% Isopropyl Alcohol, 5% Sodium Hydroxide, 5% Hydrochloric Acid, Mineral Oil, Bleach, Sulfuric Acid, Kerosene, Olive Oil, 5% Phenol, Gasoline |
| SOLID TEAK Weight: .60 lb/sq. ft., 215 lbs/roll | 0.86 Wet 0.93 Dry | (ASTM E 648) Class 1 per NFPA Life Safety Code 101 | (ASTM D 3884) Net weight Loss after 1000 revolutions: 0.12% | 1,100 psi residual compression of 0.005" | NO Change: 5% Ammonia, 5% Acetic Acid, 70% Isopropyl Alcohol, 5% Sodium Hydroxide, 5% Hydrochloric Acid, Mineral Oil, Bleach, Sulfuric Acid, Kerosene, Olive Oil, 5% Phenol, Gasoline |

For detailed technical information, please refer to www.lonseal.com.

LONSEAL, INC.
 928 E. 238th Street, Carson, CA 90745 USA
 800.832.7111 toll free | 310.830.7111 ph
www.lonseal.com



Updated: 12.03.14